

USAGE

EPISOL RM is a vapour permeable, mechanically loadable trowel mortar. Can be used as a levelling mortar for other finishes. It is suitable for ramps and can be polished.

CHEMICAL RESISTANCE

EPISOL RM has an excellent chemical resistance to alkalis, petroleum derivatives, acid, diluted organic acids, salts and solutions. For more information please contact RESIPLAST NV.

PROPERTIES

- High mechanical resistance
- Can be polished
- Vapour permeability
- Can be walked on after 12 hours
- Good smoothening qualities
- Silicone-free
- High chemical resistance
- Odourless

PROCESSING

• Preparing the application surface

Make sure the surface is clean. The recommended processing temperature for the surface, the surroundings and the material is 15 to 25°C. Do not use below 10°C.

Apply EPISOL RM on a still tacky coat of EPISOL PRIMER EM or on a sprinkled cured primer coat.

• Mixing

Stir the base (component A) evenly before use. Add the full amount of hardener (component B) and mix mechanically (300 rev/min) until both components are homogeneous. Slowly add the filler component to the mix. Mix until homogeneous.

• Application

Spread the mass with a squeegee or trowel. Press firmly and smoothen with flat trowel or power trowel.

Minimum layer thickness 5mm, optimal layer thickness is between 6 and 10mm.

After 12 hours, EPISOL RM can be finished off with EPISOL DESIGNTOP SF. Alternatively EPISOL RP/NV or EPISOL AQ PAINT can be applied (min 2 layers)

• Use

After 24 hours of curing, you can walk on the floor.

Can be mechanically loaded after 4 days.

Complete chemical resistance after 7 days at 20°C, lower temperatures will extend the curing time.

PACKAGING

EPISOL RM	Comp A	Comp B	Comp C
Set 28kg	2.2kg	0.88kg	24.92kg
Set 56kg	4.4kg	1.76kg	24.92kg x 2
Set 84kg	6.6kg	2.64kg	24.92kg x 3

TECHNICAL SPECIFICATIONS

Specific mass	2.0kg/dm ³
Colour	Sand colour
Surface	Surface slightly porous
Pressure resistance	>35N/mm ²
Flexural strength	>12N/mm ²
Tensile strength	>1.5N/mm ²
Adhesion to concrete	2.6N/mm ² (exceeds concrete cohesion)
Fire class	Class B2
Heat resistance	60°C
Layer thickness	From 5mm
Optimal layer thickness	6 – 10mm
Min. application temperature	+10°C
Min. hardening temperature	+10°C
Processing time	approx. 30 minutes at 20°C
Hardening time at 20°C	Can be walked on 12 hours Can be mechanically loaded 4 days Can be chemically loaded 7 days
Curing	Non-shrinking
Shelf life	24 months

CE CERTIFICATE


Resiplast NV, Gulkenrodestraat 3, B-2160 Wommelgem
12
EN 13813
Resin screed/coating for use indoors in buildings.

Reaction to fire	NPD
Release of corrosive substances	SR
Water permeability	NPD
Abrasion resistance (Taber)	<10 mg (CS10-1000tr-1kg)
Adhesion strength	B 1,5
Impact resistance (DIN EN ISO 6272)	>10Nm
Soundproofing	NPD
Sound absorption	NPD
Thermal resistance	NPD
Chemical resistance	NPD

USAGE

2kg/m² per mm layer thickness

APPEARANCE

A-component	Modified epoxy resins
B-component	Polyamine hardener
C-component	Dry filler
Colour	Sand colour

YOU WILL NEED TO SUPPLY

- Paint roll
- Flat trowel and squeegee
- EPISOL PRIMER EM
- Mixing bucket
- Cleaning solvent for tools: MEK SOLVENT

STORAGE

Store EPISOL RM in a dry, well ventilated storage area between 5 and 35°C.
24 months shelf life, C component unlimited shelf life.

If in doubt, contact RESIPLAST NV and provide the batch number on the package. Do not let the product get in contact with ground water, surface water or sewage systems. Dispose of contaminated packaging and remnants according to legal regulations.

SAFETY

Carefully read the safety instructions before using EPISOL RM. Products have a characteristic odour when being applied. Ensure there is sufficient ventilation, stay away from ignition sources and do not smoke. Avoid contact with skin. Eye irritation and/or sensitivity may occur during heavy vapour concentrations, inhalation and/or skin contact. Do not keep food products (food, beverages) in the same workspace. Always wear personal protective equipment according to local guidelines and regulations. Gloves and safety goggles are mandatory.

The above information is provided in good faith, but without any guarantees. The application, use and processing of the products are beyond our control and are, as such, the sole responsibility of the user/processor. In the event that Resiplast N.V. is still held liable for damages, then the claim will still be limited to the value of the goods delivered. We always aim to deliver consistently high quality goods. This version replaces all previous versions. Version 1.5 Date: 5 November 2020 4:04 pm