

## USAGE

RESITIX is a thickening agent for epoxy and polyurethane systems.

Adding RESITIX increases the thixotropy.

## CHEMICAL RESISTANCE

RESITIX has no effect on the chemical resistance of the resin.

For more information please contact RESIPLAST NV.

## PROPERTIES

- Easy to dose
- Low dust formation
- Good filling capacity
- Shrink-free hardening

## PROCESSING

### • Mixing

Stir the base (component A) evenly before use. Add the full amount of hardener (component B) and mix mechanically (300 rev/min) until both components are homogeneous. While mixing, add RESITIX until you achieve the desired consistency.

### • Use

Curing time is not affected by the addition of RESITIX.

## TECHNICAL SPECIFICATIONS

Specific mass	0.15kg/dm <sup>3</sup>
Colour	Cream beige
Odour	Odourless
Dry matter content	>90%
Min. application temperature	+10°C
Min. hardening temperature	+10°C
Processing time	approx. 20 minutes at 20°C
Hardening time at 20°C	Cured after: no effect Mechanical resistance: no effect Chemical resistance: no effect
Shelf life	1 year

## PACKAGING

RESITIX
1kg
2kg
9kg

## USAGE

0.5 to 10% in proportion to weight.

## APPEARANCE

Excipient	Cream-coloured powder
-----------	-----------------------

## YOU WILL NEED TO SUPPLY

- Cleaning solvent for tools: MEK SOLVENT

## STORAGE

RESITIX store in a dry, well ventilated storage area between 5 and 35°C. 2 year shelf life. If in doubt, contact RESIPLAST NV and provide the batch number on the package. Do not let the product get in contact with ground water, surface water or sewage systems. Dispose of contaminated packaging and remnants according to legal regulations.

## SAFETY

Carefully read the safety instructions before using RESITIX. Products have a characteristic odour when being applied. Ensure there is sufficient ventilation, stay away from ignition sources and do not smoke. Avoid contact with skin. Eye irritation and/or sensitivity may occur during heavy vapour concentrations, inhalation and/or skin contact. Do not keep food products (food, beverages) in the same workspace. Always wear personal protective equipment according to local guidelines and regulations. Gloves and safety goggles are mandatory.

The above information is provided in good faith, but without any guarantees. The application, use and processing of the products are beyond our control and are, as such, the sole responsibility of the user/processor. In the event that Resiplast N.V. is still held liable for damages, then the claim will still be limited to the value of the goods delivered. We always aim to deliver consistently high quality goods.

This version replaces all previous versions. Version 1.1  
Date: 5 November 2020 4:04 pm