PARACRYL DECO



CHARACTERISTICS

- High-quality plasto-elastic sealing kit based on an acrylic dispersion
- Easy to apply
- Can be painted quickly: "wet on wet"
- The paint used on the joint does not crack
- Mat paint remains mat
- Phthalate free

APPLICATIONS

- Specially developed to seal and fill joints with limited mobility:
 - Joints, seams and liquid-tight joints of door and window frames, window sills, staircases, skirting-boards, walls, ceilings and plasterboards.
 - Seal cracks and splits in walls. Because of its formula the product is extremely appropriate for sealing of fine joints and small cracks.
- Suitable for all porous surfaces (wood, stone, concrete, plaster...) and metal, ceramic tiles and hard PVC.

TECHNICAL CHARACTERISTICS	
Uncured sealant	
Type of sealant	Acrylic sealant
Vulcanising system	Evaporation of water
Skin forming time (23°C and 50% R.H.)	15 min
Curing speed (23°C and 50% R.H.)	0,5 mm/24 hours
Density: ISO 1183	1,13 g/ml
Processing temperature	+5°C - +40°C
Shelf life, in the original packing in dry conditions between +5°C - +25°C	Min. 12 months
Cured sealant	
Shore A hardness: ISO 868	24
Elastic recovery: ISO 7389	<50%
Deformation capability: ISO 11600	7,5%
Modulus at 100% elongation: ISO 8340	0,12 N/mm ²
% Elongation at break: ISO 8339	>300%
Temperature resistance	-20°C - +80°C.

PACKING AND COLOURS	
25 cartridges of 310 ml/box - 48 boxes/pallet	
White	

METHOD OF USE

Preparation

All surfaces should be dry, clean and free from dust or grease. When necessary, degrease with **Parasilico Cleaner**, MEK, or alcohol. It is recommended that apply a small test area prior to general use.

Primer

Diluted with water, **Paracryl Deco** can be used as a binding primer.

Application

With a gun (manual or pneumatic). The shape of the joint is important. Avoid thin layers.

This technical data sheet replaces all previous editions. The data on this sheet have been compiled according to the last laboratory report. Technical characteristics can be changed or adapted. We are not responsible for any incomplete information. Before use, one needs to ensure that the product is suitable for his application. Therefore, tests are necessary. Our general conditions apply.



Tooling

Smoothen with **DL 100** (before skin forming).

Cleaning

Tools: With water before it is dry.

Repairing

With the same product.

SAFETY

Safety data sheet available on request.

LIMITATIONS

- Cures because the water evaporates. During the first few days of curing a max. of 5% movement is allowed.
- Cannot be used for joints that are permanently exposed to water.
- Protect against frost. Do no apply in case of possible rain or frost.
- Cannot be used as a glazing kit.
- Not suitable for application outside.

TECHNICAL APPROVALS



EN 15651-1 F INT No. DoP: MP0060031



* Information sur le niveau d'émission de substances volatiles dans l'air intérieur, présentant un risque de toxicité par inhalation, sur une échelle de classe allant de A+ (très faibles émissions) à C (fortes émissions).